

Specification Sheet

Puur Microcrete

Microcrete floor finish

M surface finishes

Applied to stone slabs, levelling screed or concrete at less than 5% moisture content.

Grind existing substrate remove dust and debris.

Application: apply polymer primer over the whole substrate area - 2mm neutral base coat applied in 2 no. layers - 2mm Microcrete coloured layer applied in 2 no. layers - Puur penetrating seal & Puur finishing seal.

Thickness	Nominal: 3mm Min: 1mm Max: 5mm
In situ crushing resistance (ISCR) category	3mm max. indentation Mass of test weight: 4kg
Flatness / surface regularity	Max permissible deviation: SR2 generally