

Specification Sheet

Puur PSR

Polished concrete overlay flooring

M surface finishes

- Polymer modified cementitious screed.
- Applied to stone slabs, levelling screed or concrete at less than 5% moisture content.
- Colour: natural white or pigmented to shade.

Application

- Sand or grind of local irregularities in the existing floor to prevent unnecessary additional depth of product.
- Remove dust and debris.
- Prime prepared area to manufacturers instruction.
- PSR mix to manufacturers instruction.
- Allow cure period of 2-5 days.
- Application of penetrating and Puur PU seal to satin finish.
- Optional polish application for gloss finish.

Installation	Standard 6mm (nominal 3mm-maximum 20mm)
Colour	Natural white or pigmented with RAL or NCS base colours
Slip resistance	Regular finish dry R12 or wet R11

Floors

Flatness / Surface regularity: Max permissible deviation: SR2 generally.